

We claim:

1. A highly weather-resistant iron-based magnet powder comprising a rare-earth element, wherein particles of said magnet powder comprise uniform coating with a phosphate film to a thickness of 5 to 100nm on the average.
2. The highly weather-resistant magnet powder according to Claim 1, wherein said iron-based magnet powder comprising a rare earth element is an alloy powder selected from the group consisting of Nd-Fe-B-based and Sm-Fe-N-based powder.
3. The highly weather-resistant magnet powder according to Claim 2, wherein the particles of said Sm-Fe-N-based alloy powder are uniformly coated with a zinc film.
4. The highly weather-resistant magnet powder according to Claim 1, wherein said phosphate coating film is a composite composed of iron phosphate and another phosphate and comprises iron phosphate in an Fe/rare earth element ratio of 8 or more.
5. A resin composition for bonded magnets, comprising, as the main ingredient, the highly weather-resistant magnet powder comprising a rare-earth element, wherein particles of said magnet powder comprise uniform coating with a phosphate film to a thickness of 5 to 100nm on the average.



12. The highly weather-resistant iron-based magnet powder according to claim 1, wherein the magnet powder is formed as a compacted magnet by compacting the highly weather-resistant magnet powder to an apparent density of 85% or more of the intrinsic density.